

## SEALKOTE PATCH REPAIR IN HEAVY MONSOON



Potholes filled with water sized and shaped at the edges



SEALKOTE PATCH applied as tack coat, visible penetration even in dirt filled pothole



Next potholes filled with DBM (hot mix) into the SEALKOTE PATCH primed potholes



Fill pothole with an excess of DBM and have it suitably crowned and ready for compaction



The repaired patch is compacted with a road roller and open to traffic immediately



Apply SEALKOTE SB on the next day, but if the rains are heavy apply SEALKOTE SB immediately after compaction and open for traffic in 10 mins

These potholes were repaired at Tadi Gutta Chowk, Mundhwa road and north main road, from Koregaon Park, junction on 25<sup>th</sup> July 2013